



code	inside diameter		outside diameter		working pressure		burst pressure		weight nominal		bending radius		length max	
IVG			Ø		ps								√ [ширингиш] ▶	
	mm	inch	mm	inch	bar	psi	bar	psi	kg/m	lbs/ft	mm	inch	m	ft
1448269	6	17/72	14	0,55	20	300	60	900	0,17	0,11	60	2,4	100	328
1448277	8	5/16	17	0,67	20	300	60	900	0,23	0,16	65	2,6	100	328
1448285	10	25/64	19	0,75	20	300	60	900	0,27	0,18	80	3,2	100	328



EN

Extruded hose for fuels

Application: suitable for delivery of fuels, or for lubrication and greasing in different services.

Temperature: from -20°C (-4°F) to +90°C (+194°F).

Construction

Tube: black, seamless NBR conductive rubber, suitable to convey fuel and oils with aromatic content up to 50%.

Reinforcement: high strength synthetic fabrics.

Cover: black, seamless PVC/NBR rubber, resistant to fuel, oil, and weathering.

Electrical Resistance: tube R \leq 1x10⁶ Ω /m.

Branding: IVG RUBBER HOSE CARBUR 20 BAR W.P. - SIZE - 50 % Aromatico - BATCH NUMBER.

RU

Экструдированный топливный рукав

Применение: предназначен для подачи различного типа топлива и смазочных масел.

Температура: от -20°C до +90°C.

Конструкция

Внутренний слой: чёрный, гладкий из токопроводящего маслобензостойкого синтетического каучука, устойчивого к нефтепродуктам с ароматическим содержанием до 50%.

Усиление: высокопрочное текстильное волокно.

Покрытие: чёрное, гладкое из смеси синтетического каучука PVC/ NBR, устойчивое к нефтепродуктам, к атмосферным воздействиям и маслам.

Электрическое сопротивление: внутренний слой R≤1x106 Ω/m. Маркировка: IVG RUBBER HOSE CARBUR 20 BAR W.P. - SIZE - 50% Aromatico - BATCH NUMBER.



SAFETY INFORMATION - USER RESPONSIBILITIES

The service life of rubber hoses mainly depends on the dedicated use. Equipment and systems where the hose is installed must be designed safely. Since our hose can be designed for different applications, IVG Colbachini SpA cannot guarantee the proper functioning of the product for all situations. The analysis of the technical aspects related to specific uses must be performed by the users when choosing the product that meets their requirements. So, in relation to the variety of operating conditions and applications of the IVG hose, the user is solely responsible for the final choice of the product deemed suitable to satisfy the performance and safety requirements called for the application.

The information and technical data shown in the product data sheets must be examined by users with appropriate technical skills.

IVG Colbachini is not responsible for other uses, identified by the end user, that are different from the one shown in its catalogues, product sheets, offers, order confirmations and any recommendations attached.

An inappropriate choice of the product or a failure to follow the procedures of installation, use, maintenance and storage of the hoses may lead to a hose break and cause material damage and/or serious injury to people.

For the selection and proper use of the IVG products you can also refer to the document "Recommendations for selection, storage, use and maintenance of rubber hoses" provided by Assogomma and available on www.ivgspa.it. These recommendations are according to the international standard ISO 8331, "Plastic and rubber hoses and hose assemblies - Guidelines for selection, storage, use and maintenance."

For safety reasons, never exceed the working pressure indicated in the product data sheet.

For specific applications of rubber hoses, please refer to the legal requirements or specific standards; moreover additional recommendations for particularly critical applications are available.

For further information, contact the Marketing department (marketing@ivgspa.it).





