


Tampa

Fuel and oil suction and delivery hose



Application:

hardwall hose used for the suction and delivery of petroleum products with aromatic content up to 50%.

Wide temperature range

Aromatic content up to 50%

Length up to 120 m

Tube:

black, smooth, NBR dissipative rubber.

Reinforcement:

high strength synthetic cord, antistatic copper wire and steel helix wire.

Cover:

black, smooth (wrapped finish), NBR rubber, weathering and oil resistant.

Temperature:

from -35°C (-31°F) to +80°C (+176°F).

Branding:

continuous yellow stripe "IVG Oil (family logo)...".



Tampa



Code	Inside diameter		Outside diameter		Working pressure		Burst pressure		Weight nominal		Bending radius		Vacuum	Length max	
	mm	inch	mm	inch	bar	psi	bar	psi	kg/m	lbs/ft	mm	inch		bar	m
1497600	13	1/2	24	0,94	10	150	30	450	0,5	0,34	55	2,2	0,9	120	400
1490397	16	5/8	26,5	1,04	10	150	30	450	0,55	0,36	70	2,8	0,9	120	400
1489976	19	3/4	29,5	1,16	10	150	30	450	0,63	0,42	80	3,2	0,9	120	400
1489453	25	1	36	1,42	10	150	30	450	0,79	0,52	105	4,1	0,9	120	400
1489550	32	1-1/4	43	1,69	10	150	30	450	0,96	0,64	135	5,3	0,9	120	400
1489569	38	1-1/2	49	1,93	10	150	30	450	1,18	0,79	165	6,5	0,9	120	400
1489461	51	2	62	2,44	10	150	30	450	1,52	1,02	230	9,1	0,9	120	400
1490249	63,5	2-1/2	75,5	2,98	10	150	30	450	2,32	1,55	290	11,4	0,9	120	400
1489577	76	3	89	3,51	10	150	30	450	2,87	1,92	360	14,2	0,9	120	400
1495151	80	3-5/32	93	3,66	10	150	30	450	3,00	2,02	380	15,0	0,9	120	400
1497944	90	3-35/64	106	4,17	10	150	30	450	4,24	2,85	430	16,9	0,9	120	400
1489488	102	4	118	4,65	10	150	30	450	4,74	3,17	515	20,3	0,9	120	400
1497774	152	6	174	6,85	10	150	30	450	10,67	7,17	765	30,1	0,9	60	200

Variants available on request:

1. Softwall Tasmania hose or structure with corrugated cover.
2. Different diameters.
3. Different working pressures.

Recommended Couplings:



TW EN 14420-6



Fuel Italian Type coupling



Camlock EN 14420-7 (DIN 2828)

SPECIAL DETAILS

WARNINGS AND PRECAUTIONS

Rubber hoses have a service life proportional to their usage.

The equipment and systems where the hose is installed must be designed to ensure safe operation. Given the wide range of possible applications, IVG Colbachini does not guarantee suitability for all specific uses. The selection of the most appropriate product for the intended application, ensuring the required performance and safety standards, is the sole responsibility of the user.

IVG Colbachini shall therefore not be held liable for any use other than those indicated in its catalogues, product data sheets, quotations, order confirmations, or any accompanying recommendations.

Improper product selection and/or use, or failure to comply with installation, operation, maintenance, and storage procedures, may result in hose failure and cause damage to property or personal injury.

IVG Colbachini manufactures and markets both assembled hoses and hoses supplied without fittings.

Assembled Hoses

Before being placed on the market, the hose assembly is subjected by IVG to manufacturing control tests carried out by qualified personnel.

IVG declines all responsibility for any subsequent modifications, disassembly, or reinstallation of fittings performed by the user, as well as for uses that differ from those indicated in the product data sheet or in the absence of maintenance programs and periodic inspections.

Hoses and Fittings as spare parts

The user is responsible for assembling the hose and fittings, ensuring proper hose/fitting compatibility and compliance with the technical specifications for use. It is recommended that the hose assembly be subjected to a pressure tightness test carried out by qualified personnel.

IVG declines all responsibility in this regard.

Precautions

For proper selection and correct use of IVG products, reference should also be made to the recommendations issued by Assogomma, available at www.ivgspa.it, in accordance with ISO 8331 regarding installation, maintenance, methods and duration of use, as well as fitting stability and tightness.

For safety reasons, the working pressure indicated in the product technical data sheet must never be exceeded.

In general, continuous operation at maximum allowable pressure and/or temperature may significantly reduce the hose service life. Regular inspections and hydrostatic testing at the specified test pressure must therefore be carried out. Hydrostatic tests must be performed by adequately trained personnel using suitable equipment and in accordance with recognized testing standards.

For specific applications of rubber hoses, reference should be made to applicable legal requirements or compliance standards. Additional recommendations are available for particularly critical applications. For further information, please contact info@ivgspa.it.