


Orinoco HP

Рукав для пескоструйки



Нормативно-правовые акты:

Превышает норму ISO 3861:2008.
абразивостойкость внутреннего слоя
соответствует норме ISO 4649: 45 +/- 5mm³.

Применение:

напорный особо абразивостойкий рукав для подачи особо абразивных сыпучих материалов, таких как кварцевый песок, стальная дробь, корунд, стекло и пр. Специальный антистатический состав каучука позволяет избежать электростатических разрядов.

Отличная устойчивость к абразиву
Гибкий и легкий в использовании
Абразивостойкость ISO 4649: 45+/- 5 mm³



Внутренний слой:

чёрный, гладкий из смеси синтетического и натурального каучука SBR/NR антистатический, повышенной абразивостойкости гарантирующей долгосрочное использование.

Усиление:

высокопрочный синтетический корд.

Покрытие:

чёрное, гладкое (с отпечатком текстильного банджа), из синтетического каучука антистатическое, устойчивое к истиранию.

Температура:

от -40°C до +80°C.

Маркировка:

красная маркировочная лента "IVG Abr (логотип сферы применения)...".



Orinoco HP



Код	Внутренний диаметр		Внешний диаметр		Рабочее давление		Разрывное давление		Номинальный вес		Максимальная длина	
	mm	inch	mm	inch	bar	psi	bar	psi	kg/m	lbs/ft	m	ft
1471007	13	1/2	27	1,06	12	180	42	630	0,48	0,33	120	400
1479091	16	5/8	30	1,18	12	180	42	630	0,56	0,38	120	400
1472208	19	3/4	33	1,30	12	180	42	630	0,64	0,43	120	400
1471589	25	1	39	1,54	12	180	42	630	0,78	0,52	120	400
1470191	32	1-1/4	48	1,89	12	180	42	630	1,11	0,75	120	400
1471570	32	1-1/4	50	1,97	12	180	42	630	1,32	0,88	120	400
1472283	38	1-1/2	56,5	2,23	12	180	42	630	1,49	1,01	120	400
1471627	42	1-24/32	60,5	2,38	12	180	42	630	1,61	1,08	120	400
1471341	60	2-3/8	80	3,15	12	180	42	630	2,37	1,59	120	400

Возможные варианты по запросу:

1. Другие диаметры.

Рекомендуемые соединения:



Mortar coupling



Sandblasting



Plaster coupling CP to be applied with screws

SPECIAL DETAILS

SAFETY INFORMATION – USER RESPONSIBILITIES

The service life of rubber hoses mainly depends on the dedicated use. Equipment and systems where the hose is installed must be designed safely. Since our hose can be designed for different applications, **IVG Colbachini** cannot guarantee the proper functioning of the product for all situations.

The analysis of the technical aspects related to specific uses must be performed by the users when choosing the product that meets their requirements. So, in relation to the variety of operating conditions and applications of the IVG hose, the user is solely responsible for the final choice of the product deemed suitable to satisfy the performance and safety requirements called for the application.

The information and technical data shown in the product data sheets must be examined by users with appropriate technical skills. IVG Colbachini is not responsible for other uses, identified by the end user, that are different from the one shown in its catalogues, product sheets, offers, order confirmations and any recommendations attached.

An inappropriate choice of the product or a failure to follow the procedures of installation, use, maintenance and storage of the hoses may lead to a hose break and cause material damage and/or serious injury to people.

For the selection and proper use of the IVG products you can also refer to the document "Recommendations for selection, storage, use and maintenance of rubber hoses" provided by Assogomma and available on www.ivgspa.it. These recommendations are according to the international standard ISO 8331, "Plastic and rubber hoses and hose assemblies - Guidelines for selection, storage, use and maintenance."

For safety reasons, never exceed the working pressure indicated in the product data sheet.

For specific applications of rubber hoses, please refer to the legal requirements or specific standards; moreover, additional recommendations for particularly critical applications are available.

For further information, contact the Marketing department (marketing@ivgspa.it).